

CYCOLACT™ RESIN MG94F

REGION EUROPE

DESCRIPTION

Superior flow, injection molding ABS. Good impact. For thin-wall applications. FDA compliant.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	40	MPa	ISO 527
Tensile Stress, break, 5 mm/min	35	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Stress, break, 50 mm/min	35	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	35	%	ISO 527
Tensile Strain, yield, 50 mm/min	2.2	%	ISO 527
Tensile Strain, break, 50 mm/min	45	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	65	MPa	ISO 178
Flexural Modulus, 2 mm/min	2450	MPa	ISO 178
Ball Indentation Hardness, H358/30	95	MPa	ISO 2039-1
Hardness, Rockwell R	129	-	ISO 2039-2
IMPACT			
Izod Impact, notched 80*10*4 +23°C	18	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	23	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m ²	ISO 179/1eA
THERMAL			
CTE, 23°C to 60°C, flow	8.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.7E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	99	°C	ISO 306
Vicat Softening Temp, Rate B/120	100	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	91	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	80	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Density	1.04	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.16	%	ISO 62
Melt Volume Rate, MVR at 220°C/10.0 kg	39	cm ³ /10 min	ISO 1133
Melt Flow Rate, 230°C/3.8 kg	11.7	g/10 min	ASTM D1238
Melt Flow Rate, 220°C/5.0 kg	12	g/10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-102071280	-	-
Glow Wire Flammability Index 650°C, passes at	3.2	mm	IEC 60695-2-12

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING			
Drying Temperature	85 – 95	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	220 – 260	°C	
Nozzle Temperature	210 – 250	°C	
Front - Zone 3 Temperature	220 – 260	°C	
Middle - Zone 2 Temperature	220 – 260	°C	
Rear - Zone 1 Temperature	200 – 240	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	40 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.