

VALOX™ FR RESIN ENH3500

REGION EUROPE

DESCRIPTION

VALOX ENH3500 is an unreinforced, non-chlorinated/brominated flame retardant Polybutylene Terephthalate (PBT) injection moldable grade with excellent chemical resistance. It has a UL94V0@0.80mm flame rating. This is a good candidate for a variety of applications needing a sustainable FR PBT solution.

TYPICAL PROPERTY VALUES

Revision 20230519

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	44	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	42	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	10	%	ASTM D638
Tensile Modulus, 5 mm/min	3150	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	77	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2750	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	39	MPa	ISO 527
Tensile Stress, break, 50 mm/min	38	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	8	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	70	MPa	ISO 178
Flexural Modulus, 2 mm/min	2700	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	40	J/m	ASTM D256
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	160	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	60	°C	ASTM D648
Vicat Softening Temp, Rate B/50	170	°C	ASTM D1525
CTE, -40°C to 95°C, flow	8.00E-05	1/°C	ASTM E831
CTE, -40°C to 95°C, xflow	8.00E-05	1/°C	ASTM E831
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	170	°C	ISO 306
Vicat Softening Temp, Rate B/50	170	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	60	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Bf

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Elec ⁽²⁾	150	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	105	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	150	°C	UL 746B
PHYSICAL ⁽¹⁾			
Moisture Absorption, (23°C/50% RH/24 hrs)	0.08	%	ASTM D570
Water Absorption, (23°C/24hrs)	0.35	%	ASTM D570
Specific Gravity	1.31	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow ⁽³⁾	1.8 – 2.8	%	SABIC method
Density	1.31	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 250°C/2.16 kg	20	cm ³ /10 min	ISO 1133
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
ELECTRICAL ⁽¹⁾			
Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Comparative Tracking Index ⁽²⁾	525	V	IEC 60112
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 4	≥0.8	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥0.8	mm	UL 746A
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-100208982	-	-
UL Recognized, 94-5VA Flame Class Rating	≥3	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	≥2	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.8	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	700	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	700	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	700	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.8 mm	750	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.8 mm	960	°C	IEC 60695-2-12
Oxygen Index (LOI)	31	%	ASTM D2863
Oxygen Index (LOI)	31	%	ISO 4589
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	230 – 255	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	235 – 250	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	230 – 240	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.