

Advanced PP H139

Polypropylene Homopolymer

Product Description

Advanced PP H139 is a homopolymer used for general purpose injection molding applications. It exhibits good flow and stiffness. Advanced PP H139 typical applications are in furniture and houseware.

General

Typical Application

- Furniture
- Housewares
- Rigid Packaging

Product Features

- Good Flow
- Good Stiffness

Regulatory Status

- Compliance with Reach regulation
- Compliance with FDA regulation
- Compliance with European Union Regulation (EU) 10/2011

Type	Properties	Unit	Value	Test Method
Resin	Density	g / cm ³	0.9	ISO 1183
	Melt Flow Rate (MFR 230°C / 2.16 Kg)	g / 10 min	23	ISO 1133
Mechanical	Flexural Modulus	MPa	1400	ISO 178
	Tensile Stress at Yield (50 mm/min)	MPa	35	ISO 527-2
	Tensile Strain at Yield (50 mm/min)	%	11	ISO 527-2
	Charpy Impact Strength Notched (+23°C)	kJ / m ²	3	ISO 179/1eA
Thermal	Vicat Softening Temperature (A/50, 10 N)	°C	154	ISO 306
	Heat Deflection Temperature B ₁ (0.45 MPa)	°C	85	ISO 75-2

Note:

- Values presented in this technical data sheet are typical values obtained from product testing and should not be construed as product specifications or analytical certifications. These values are provided for reference only.
- It is recommended to dry the resin before use. Moisture condensation may arise under fluctuating temperatures and high humidity.
- Appropriate storage conditions must be observed. Resin must be protected from direct exposure to sunlight, temperatures above 40°C, and high humidity.